

Capa™ Polyols

Partner for your future needs

Aliphatic polyester polyols for high performance polyurethane applications

We believe a greater flexibility in the design of key raw materials is required as the demand for higher performing polyurethanes increases.

We offer a wide range of Capa™ polycaprolactone polyols, designed for CASE applications, to meet your needs. Through close customer collaborations and innovations we are continuously developing our product range to even further enhance the benefits that polyurethane systems can offer. Together we can shape the future with Capa™.

Coatings

- Best-in-class performance properties
- Outstanding lifelong resistance
- High quality finish & appearance


Adhesives/Sealants

- Exceptional strength and durability
- Penetrates even difficult substrates
- Highly resistant to change

Elastomers

- Durability and long lasting performance
- Flexible in production and designing materials
- Consistent quality of product

Capa application areas



Low Viscosity Capa™ Polyols

Aliphatic polyester polyols ideal for high quality Polyurethane coatings, adhesives and cold cure elastomers

Product type	Capa™ Grade	Appearance on Storage (18°C)	OH Value*	Func.	Mol. Weight*	Viscosity @25°C (mPa.s)*	Viscosity @30°C (mPa.s)*	Viscosity @60°C (mPa.s)*	Viscosity @80°C (mPa.s)*
Liquid Diol	2043	Clear Liquid	280	2	400	240	190	40	<20
Liquid Diol	2047A	Clear Liquid	280	2	400	230	180	40	<20
Liquid Diol	2054	Hazy Liquid	208	2	550	310	240	60	<20
Liquid Diol	2065	Hazy Liquid	173	2	650	585	340	80	<20
Semi-Solid Diol	2077A	Soft Wax	160	2	750	Solid	440	85	<20
Semi-Solid Diol	2085	Soft Wax	140	2	830	2700	500	100	40
Semi-Solid Diol	2100	Soft Wax	112	2	1000	1200	620	150	75
Semi-Solid Diol	2101A	Soft Wax	112	2	1000	Solid	620	150	75
Semi-Solid Diol	7201A	Soft Wax	56	2	2000	Solid	1500	315	185
Liquid Diol	8025D	Clear Liquid	56	2	2000	6500	4600	1000	-
Liquid Triol	3031	Clear Liquid	561	3	330	1600	1200	170	50
Liquid Triol	3050	Clear Liquid	337	3	500	1200	880	160	65
Liquid Triol	3091	Clear Liquid	187	3	900	1250	930	165	70
Liquid Triol	8025E	Clear Liquid	84	3	2000	5300	-	700	-
Liquid Tetrol	4101	Clear Liquid	224	4	1000	1800	1400	260	120

* Median average of the range

Capa™ Polyols

Aliphatic polyester polyols ideal for high quality Polyurethane elastomers and adhesives

Product type	Capa™ Grade	Appearance on Storage (18°C)	OH Value*	Func.	Mol. Weight*	Viscosity @25°C (mPa.s)*	Viscosity @30°C (mPa.s)*	Viscosity @60°C (mPa.s)*	Viscosity @80°C (mPa.s)*
Semi-Solid Diol	2077A	Soft Wax	160	2	750	Solid	440	85	<20
Semi-Solid Diol	2085	Soft Wax	140	2	830	2700	500	100	40
Semi-Solid Diol	2100	Soft Wax	112	2	1000	1200	620	150	75
Semi-Solid Diol	2101A	Soft Wax	112	2	1000	Solid	620	150	75
Semi-Solid Diol	2125	Soft Wax	93	2	1200	Solid	Solid	175	60
Semi-Solid Diol	2161A	Wax	70	2	1600	Solid	Solid	300	150
Solid Diol	2201	Wax	56	2	2000	Solid	Solid	480	175
Solid Diol	2201A	Wax	56	2	2000	Solid	Solid	480	175
Solid Diol	2203A	Wax	56	2	2000	Solid	Solid	450	230
Solid Diol	2205	Wax	56	2	2000	Solid	Solid	435	220
Solid Diol	2209	Wax	56	2	2000	Solid	Solid	380	200
Semi-Solid Diol	7201A	Soft Wax	56	2	2000	Solid	1500	315	185
Solid Diol	7203	Wax	56	2	2000	Solid	Solid	1000	575
Solid Diol	2302A	Wax	37	2	3000	Solid	Solid	1100	480
Solid Diol	2402	Wax	28	2	4000	Solid	Solid	1700	930
Solid Diol	2803	Wax	14	2	8000	Solid	Solid	8600	5300
Solid Triol	3201	Wax	84	3	2000	Solid	Solid	360	200

* Median average of the range

