

HAITUNG GROUP LTD

PVA Grades & Specifications

Grades	Hydrolysis (mol%)	Volatiles (%)	Viscosity (mpa.s)	Ash (wt%)	PH Value	Purity (wt%)
088-03	87.0 – 89.0	≤5.0	3.0-4.0	≤0.7	5-7	≥93.0
088-04	87.0 – 89.0	≤5.0	4.0-4.5	≤0.7	5-7	≥93.0
098-04	98.0-98.8	≤5.0	4.0-5.0	≤0.5	5-7	≥93.5
088-05	87.0 – 89.0	≤5.0	4.5-6.0	≤0.5	5-7	≥93.5
098-05	98.0-99.0	≤5.0	5.0-6.5	≤0.5	5-7	≥93.5
098-10	97.0-99.0	≤5.0	8.0-12.0	≤0.5	5-7	≥93.5
088-13	87.0 – 89.0	≤5.0	12.0-14.0	≤0.5	5-7	≥93.5
098-15	98.0 -99.0	≤5.0	13.0-17.0	≤0.5	5-7	≥93.5
093-16	92.5-94.5	≤5.0	14.5-18.5	≤0.5	5-7	≥93.5
098-20	98.0-99.0	≤5.0	18.0-22.0	≤0.5	5-7	≥93.5
088-20	87.0 – 89.0	≤5.0	20.5-24.5	≤0.4	5-7	≥93.5
092-20	91.0-93.0	≤5.0	21.0-27.0	≤0.5	5-7	≥93.5
096-27	96.0-98.0	≤5.0	23.0-29.0	≤0.5	5-7	≥93.5
098-27	98.0 – 99.0	≤5.0	23.0-29.0	≤0.5	5-7	≥93.5
088-26	87.0 – 89.0	≤5.0	24.0-28.0	≤0.5	5-7	≥93.5
095-28	94.0-96.0	≤5.0	26.0-30.0	≤0.5	5-7	≥93.5
098-30	98.0 – 99.0	≤5.0	28.0-32.0	≤0.5	5-7	≥93.5
088-35	87.0 – 89.0	≤5.0	29.0-34.0	≤0.3	5-7	≥93.5
088-50	87.0 – 89.0	≤5.0	45.0-55.0	≤0.3	5-7	≥93.5
097-60	96.0-98.0	≤5.0	56.0-66.0	≤0.5	5-7	≥93.5
098-60	98.0 – 99.0	≤5.0	58.0-68.0	≤0.5	5-7	≥93.5
097-70	96.0 – 98.0	≤5.0	66.0-76.0	≤0.5	5-7	≥93.5
098-75	98.0 – 99.0	≤5.0	70.0-80.0	≤0.5	5-7	≥93.5

ADDRESS:20F JINRONG BUILDING,EAST OF SHENGLI STR.,261041 WEIFANG
 SHANDONG CHINA

TEL:+86 536 8275145 FAX:+86 536 8275045

WEB:WWW.HAITUNGCHEM.COM